



CLINKER SR



Chemical characteristics

Elements	Moyen %
SiO ₂	21.04
Al ₂ O ₃	3.85
Fe ₂ O ₃	4.64
CaO	66.41
MgO	1.31
SO ₃	1.61
Na ₂ O	0.2
K ₂ O	0.75
CaO free lime	1.26
C ₃ S - Bogue calculation	84.34
C ₂ S - Bogue calculation	0
C ₃ A - Bogue calculation	2.34
C ₄ AF - Bogue calculation	14.13

CLINKER OPC



Chemical characteristics

Elements	Moyen %
SiO ₂	21.12
Al ₂ O ₃	5.18
Fe ₂ O ₃	4.00
CaO	65.21
MgO	1.17
SO ₃	1.65
Na ₂ O	0.23
K ₂ O	1.11
CaO free lime	1.53
C ₃ S - Bogue calculation	69.7
C ₂ S - Bogue calculation	8.34
C ₃ A - Bogue calculation	6.96
C ₄ AF - Bogue calculation	12.16