



## CLINKER OPC



### Caractéristiques chimiques

Eléments	Moyen %
SIO2	20.6
Al2O3	5.5
Fe2O3	3.5
CaO	65.5
MgO	1.1
SO3	1.7
Na2O	0.1
K2O	0.93
CaOLibre	1.42
C3S - Bogue	61.48
C2S - Bogue	13.27
C3A - Bogue	8.71
C4AF - Bogue	10.52



### Chemical characteristics

Elements	Moyen %
SIO2	20.6
Al2O3	5.5
Fe2O3	3.5
CaO	65.5
MgO	1.1
SO3	1.7
Na2O	0.1
K2O	0.93
CaO free lime	1.42
C3S - Bogue calculation	61.48
C2S - Bogue calculation	13.27
C3A - Bogue calculation	8.71
C4AF - Bogue calculation	10.52