



## CLINKER SR3



### Caractéristiques chimiques

| Eléments                       | Moyen % |
|--------------------------------|---------|
| SiO <sub>2</sub>               | 21.09   |
| Al <sub>2</sub> O <sub>3</sub> | 4.31    |
| Fe <sub>2</sub> O <sub>3</sub> | 5.44    |
| CaO                            | 65.67   |
| MgO                            | 0.72    |
| SO <sub>3</sub>                | 1.7     |
| Na <sub>2</sub> O              | 0.08    |
| K <sub>2</sub> O               | 0.71    |
| CaOLibre                       | 1.52    |
| C <sub>3</sub> S - Bogue       | 62.15   |
| C <sub>2</sub> S - Bogue       | 12.4    |
| C <sub>3</sub> A - Bogue       | 2.22    |
| C <sub>4</sub> AF - Bogue      | 16.5    |



### Chemical characteristics

| Elements                              | Moyen % |
|---------------------------------------|---------|
| SiO <sub>2</sub>                      | 21.09   |
| Al <sub>2</sub> O <sub>3</sub>        | 4.31    |
| Fe <sub>2</sub> O <sub>3</sub>        | 5.44    |
| CaO                                   | 65.67   |
| MgO                                   | 0.72    |
| SO <sub>3</sub>                       | 1.7     |
| Na <sub>2</sub> O                     | 0.08    |
| K <sub>2</sub> O                      | 0.71    |
| CaO free lime                         | 1.52    |
| C <sub>3</sub> S - Bogue calculation  | 62.15   |
| C <sub>2</sub> S - Bogue calculation  | 12.4    |
| C <sub>3</sub> A - Bogue calculation  | 2.22    |
| C <sub>4</sub> AF - Bogue calculation | 16.5    |